

Sun States Inventory

Click Browser "Back" Button to Return to Website

Plant Location	Tag #	Product	Gauge	Width	Length	Weight	Grade	Rb	ID	OD	Visual Inspection	
JMH	Huger, SC	2005157	Cold Rolled	.014	28.000		4,332	DS	41	.013	.014	No Visible Defects
JMH	Huger, SC	2005227	Cold Rolled	.0155	29.000		8,410	CS-B	56	.016	.016	No Visible Defects
TRC	Wilmerding, PA	2002764	Cold Rolled	.016	60.062		3,050	CS-B	68	.016	.016	Storage Rust
TRC	Wilmerding, PA	2002765	Cold Rolled	.016	60.062		2,775	CS-B	68	.016	.016	Storage Rust
CHI	Gary, IN	2002383	Cold Rolled	.017	57.620		1,420	CS-B	62	.017	.018	Subject to Rust
CHI	Gary, IN	2004273	Cold Rolled	.018	2.090		790	CS-B	62	.0190	.0190	Subject to Buckles (3 Coils)
CHI	Gary, IN	2004288	Cold Rolled	.018	15.188		1,345	CS-B	62	.0180	.0180	Subject to Light Rust (5 Coils)
PMT	Chicago, IL	2004958	Cold Rolled	.018	43.000		13,790	CS-B	62	.0190	.0190	Heavy Center Buckle
JMH	Huger, SC	2004982	Cold Rolled	.018	46.000		36,140	HS	59	.017	.018	Subject to Buckles
CHI	Gary, IN	2002392	Cold Rolled	.018	46.680	64.000	5,480	CS-B	62		.019	Storage Rust
CHI	Gary, IN	2005033	Cold Rolled	.018	58.310		9,930	CS-B	68	.0180	.0180	No Visible Defects
SMP	Lawrenceville, GA	2002119	Cold Rolled	.019	37.000		4,390	DS		.021	.021	No Visible Defects
COL	Atlanta, GA	2005196	Cold Rolled	.019	44.125		8,280	DS	37	.019	.019	No Visible Defects
COL	Atlanta, GA	2003043	Cold Rolled	.023	4.320		580	CS-B	62	.0230	.0230	Heavy Rust Throughout (3 Coils)
COL	Atlanta, GA	2003045	Cold Rolled	.023	4.320		780	CS-B	62	.0230	.0230	Heavy Rust Throughout (4 Coils)
COL	Atlanta, GA	2003046	Cold Rolled	.023	4.320		770	CS-B	62	.0230	.0230	Heavy Rust Throughout (4 Coils)
CHI	Gary, IN	2003843	Cold Rolled	.024	48.000		18,460	CS-B	62	.0240	.0230	Chain damage to ID; ID has Rust;
CHI	Gary, IN	2004825	Cold Rolled	.024	48.060		22,640	DS	49	.024	.024	Spotty Light Rust (Tension
CHI	Gary, IN	2003844	Cold Rolled	.024	48.250		15,740	CS-B	62	.0240	.0240	Chain damage to ID; Spotty
COL	Atlanta, GA	2001707	Cold Rolled	.025	40.500		8,840	DDS	35	.0250	.0250	No Visible Defects
ALM	Cartersville, GA	2003443	Cold Rolled	.025	59.375		17,680	CS-B	62	.025	.025	Spot Rust on ID/OD
TMS	Tampa, FL	2004959	Cold Rolled	.026	36.000		19,140	CS-B	68	.0267	.0269	Subject to Stain; Light Rust Both
TMS	Tampa, FL	2004960	Cold Rolled	.026	36.000		19,100	CS-B	68	.0265	.0267	Subject to Scattered Rust
COL	Atlanta, GA	2004682	Cold Rolled	.026	44.500		5,415	DS	55	.0290	.0290	No Visible Defects
CHI	Gary, IN	2003182	Cold Rolled	.026	45.500		3,130	CS-B	45	.028	.028	Lite Speck Rust on OD ; Lite
ALM	Cartersville, GA	2003618	Cold Rolled	.026	46.000		12,360	DS		.024	.027	Lite Chain and Edge Damage -
COL	Atlanta, GA	2004097	Cold Rolled	.026	60.125	120.125	4,125	CS-B	68		.026	No Visible Defects

Sun States Inventory

Click Browser "Back" Button to Return to Website

Plant Location	Tag #	Product	Gauge	Width	Length	Weight	Grade	Rb	ID	OD	Visual Inspection	
JMH	Huger, SC	2005156	Cold Rolled	.027	38.250	51.625	2,766	DDS	36		.027	No Visible Defects
JMH	Huger, SC	2005158	Cold Rolled	.027	51.625		24,520	DDS	36	.027	.028	No Visible Defects
COL	Atlanta, GA	2004305	Cold Rolled	.027	61.125		3,765	CS-B	62	.0290	.0290	No Visible Defects
COL	Atlanta, GA	2004309	Cold Rolled	.029	48.125		7,020	CS-B	62	.0320	.0300	No Visible Defects
COL	Atlanta, GA	2002323	Cold Rolled	.030	5.000		3,985	HS	78	.0310	.031	No Visible Defects (4 Coils)
COL	Atlanta, GA	2002325	Cold Rolled	.031	5.000		3,970	HS	78	.031	.031	No Visible Defects (4 Coils)
COL	Atlanta, GA	2003610	Cold Rolled	.033	60.000		13,230	CS-B		.0310	.0310	N/A
COL	Atlanta, GA	2003036	Cold Rolled	.039	26.000		7,940	HSLA	72	.0400	.0400	Heavy Rust Throughout
GPM	Franklin, OH	2004345	Cold Rolled	.040	36.000		18,700	CS-B	68	.0440	.0420	Rust ID/OD
COL	Atlanta, GA	2004442	Cold Rolled	.043	3.875		910	DDS	34	.0470	.0470	No Visible Defects (2 Coils)
CHI	Gary, IN	2005106	Cold Rolled	.044	42.250	57.000	2,333	DDS	43		.044	Storage Rust ; No Visible Defects
COL	Atlanta, GA	2004565	Cold Rolled	.045	2.000		825	DDS	34	.047	.0460	No Visible Defects
COL	Atlanta, GA	2003118	Cold Rolled	.045	42.250	55.000	4,100	DDS	34		.045	Lite Rust on Top Sheet
CHI	Gary, IN	2003178	Cold Rolled	.052	25.370		5,350	CS-B	45	.053	.053	No visible Defects (Skidded)
MPT	Tampa, FL	2003395	Cold Rolled	.054	48.000		3,795	CS-B	68	.056	.056	N/A
COL	Atlanta, GA	2004431	Cold Rolled	.103	2.625		1,095	CS-B	45	.1030	.1030	No Visible Defects
COL	Atlanta, GA	2003881	Cold Rolled	.111	56.675		18,180	DDS	34	.111	.110	Storage Rust ; Balance No Visible
COL	Atlanta, GA	2002131	Cold Rolled	.112	48.250	144.000	2,850	N/A			.114	Subject to Rust